

JPL TERRASHIELD FINE

JPL TERRASHIELD FINE

A flexible, elastomeric paintable plaster for seamless, crack-resistant, waterproof finishes.



TECHNICAL ADVANTAGES

- Crack - Resistant
- Elastomeric & Flexible
- Fire Retardent
- Cost & Time Efficient
- Eco-Friendly
- Ready-to-Use
- No Curing
- Paintable Properties
- Anti-Fungal

PACKAGE AVAILABLE

Shelf Life - 18 Months

Color - White



20 KG Bag



30 Kg Bucket

APPLICATION PROCEDURE

Note:

- Load the JPL Terrashield Fine on Mivan, Pre-cast Construction Cement/Gypsum Plastered Walls or Pre-painted walls with a trowel or roller in 2 coats up to a maximum thickness of 2 mm.
- Refer to the next page for 45 GSM Nylon Mesh Applicability.

Procedure to follow for Application:

- Apply the first coat of Terrashield & allow it to dry for at least 6 to 8 hours.
- Apply 45 GSM Nylon Mesh while the first coat is wet
- Apply the second coat of Terrashield with a roller or a trowel.
- Remove the excess material with emery paper (no. 320) by light sanding vertically and horizontally to get a smooth, seamless surface.
- The surface is ready to be painted within 96 hours after completion of the second coat.

NOTE:

- First fill cracks, then apply wall coatings.
- For AAC Blocks and precast panels with a width of less than or equal to 2 ft., embed a 45 GSM nylon mesh across the surface between the first & second coat while the first coat surface is wet.
- On Dry Wall Joints/Pre-cast Joints/ Construction Joints in Mivan embed a 45 GSM mesh with a maximum 150 mm width on the joints covering the joint area completely, between the first coat & second coat while the first coat surface is wet.
- On AAC Blocks, Drywall Pre-cast joints, etc., the mesh must be terminated on the ceiling up to 100 mm (only if the joint terminates at ceiling level).
- Overlapping of the mesh must be avoided on the vertical joints of the mesh.
- On all corners and joints of walls, beams, columns and ceiling, the mesh has to be overlapped to a width of at least 100 mm.
- Only Premium Emulsion must be used for the interiors over Terrashield, and only Anti-Fungal Emulsion must be used for the exteriors over Terrashield where the sub-sub-strate is of AAC Blocks, whether plastered with Gypsum or sand-cement mortar (Interiors or Exteriors) or Dry Walls or Walls with joints.
- On other substrate surfaces, such as MIVAN, RCC, and Cement Plastered (on Mivan/Red Bricks), you may use any paint over Terrashield. Paints may include OBD, Internal/External Emulsion, Premium Emulsions, etc.
- The JPL Terrashield Fine properties are such that after application, the material may sink or form bubbles, which may lead to slight 0.5 -1mm undulations on the surface. Sinking is due to the increment of cracks in the substrate or the sub-substrate. Bubbling is due to the trapped air expanding. This does not constitute product failure. Note: In the above-mentioned event, JPL Terrashield Fine is to be applied again only on the localized areas.
- Breaking of 45 GSM nylon mesh does not constitute product failure, but signifies other serious structural and/or construction issues.

NABL TEST RESULTS

Carried out as per ASTM Standards by SriRam and Eurofin Labs

Class 1 or A	Fire Retardant Surface rating
3.2 MPA	Compressive Strength
5.8 MPA	Tensile Strength
1.9 MPA	Flexural Strength
24.3% Absorption	after submerged for 24hrs.
1.0 MPA	Pull of Strength

COVERAGE

DESCRIPTION	MAX. THICKNESS	AREA IN SQ.FT
Coarse Cement Plastered	2.00 mm	80 – 100
Fine Sand Plastered	2.00 mm	100 - 120
Gypsum Plastered	2.00 mm	150 - 175
RCC Ceiling Surface without Mesh only rendering	2.00 mm	140 - 175
RCC Wall	2.00 mm	140 – 175